

DORUS KS 350

EVA Hotmelt Adhesive for Edgebanding Unfilled

Characteristics

- Medium viscosity
- Universal hotmelt adhesive
- Very clean working
- Produces tight joints virtually not visible
- Very high heat resistance
- High glue mileage
- Very good wetting
- Permits smooth surfaces even with very flexible edging materials

Fields of application

- Edgebanding as from feedrates of 15 m/min
- Edging material: veneer, melamine, polyester, HPL*, PVC*, ABS*, PP*
**Suitability depends on the individual characteristics of the edging material and how it is primed.*
- Softforming even with difficult-to-bond profiles
- Suitable for processing centres (BAZ) with direct application

Technical data

| | |
|---|---|
| Softening point (Ring & Ball): | approx. 125 °C (257 °F) |
| Viscosity (Brookfield): | approx. 175 000 mPa·s / 180 °C (356 °F) approx. 90 000 mPa·s / 200 °C (392 °F) |
| Heat resistance: | approx. 100 °C (212 °F) |
| <i>tested with 0.6 mm oak veneer using the DORUS method of increasing temperature</i> | |

Instructions for use

| | |
|--|-----------------------------|
| Recommended working temperature | |
| in the melting container: | 190 - 210 °C (374 - 410 °F) |
| at the application roller/slot nozzle: | 190 - 210 °C (374 - 410 °F) |

Colour available

Transparent, white

Delivery form

Granules

Storage


Shelf life of at least 1 year if stored in a cool and dry place.

Labelling

Hazardous warning labelling according to GefStoffV and EU Directives not required.

Safety

Hotmelt adhesives give off vapours even when the specified working temperature is not exceeded. The smells emitted may often cause irritation. When the specified temperatures are considerably exceeded over a longer period of time, there is the additional danger of decomposition products being given off. Therefore measures to draw off the vapours need to be taken, e.g. through the provision of extraction equipment.



03/00

The information provided herein, especially recommendations for the usage and applications of our products, is based on our knowledge and experience. Due to different material used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regards to the required process and applications. We do not accept any liability with regards to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.